

# AFCONA - 3250



## Chemical Composition

Special organically modified polysiloxane.

## Product general description

Additive designed to perform the highest slip in all solvent based coating without foam stabilizing property.

## Product Properties:

AFCONA-3250 is special developed for all solvent based systems where the slip is the most important factor and foam stabilizing effect is undesired. AFCONA – 3250 belong the same family AFCONA – 3230. AFCONA-3230 effective only in polyurethane coating but AFCONA-3250 effective in all solvent based coating.

Most polysiloxane with good transparency stabilize foam, or, when not stabilizing foam affect the transparency of the coating. Thus AFCONA-3250 fulfill all the needs of most paint formulators where it gives very good slip, no foam stabilizing effect and good transparency.

Duo to the excellent properties of AFCONA-3250 is very suitable for use in:

- 1) all wood coatings like NC, Acid curing, PU, and UV. Slip is always one of the most important measurements for wood coatings.
- 2) Top coats in plastic coating applications like mobile phone and those plastic items that frequently touched by our hand. In these applications, slip is very important.
- 3) UV coatings, where it gives very good slip and leveling without influence the clarity of the paint film.
- 4) Refinish topcoat that based on polyurethane.
- 5) Other paint systems where high slip is desired.

AFCONA-3250 is a very suitable leveling agent in epoxies as it will not stabilize foam but act as very good defoamer in such systems.

Note: AFCONA-3250 will become slightly hazy at temperatures below 5°C. This will not influence the quality.

## Product Specification

Non-volatile matter	≥95% (120°C, 0.5h)
Density	0.98 – 1.01g/cm <sup>3</sup> (20°C)
The refractive index	1.425 – 1.445 (25°C)
Flash point	>100°C
Gardner color	Max.4
Appearance	Transparent to slightly yellowish liquid (25°C)
Note: It will be slightly hazy below 5°C	

## Addition and dosage

0.05 – 0.50% on total formulation. In general under normal conditions, the dosage is 0.10 – 0.30% based on total formulation.

## Incorporation

AFCONA-3250 can be added at any stage of production process.

## Storage

AFCONA-3250 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

## Packaging

30kg and 200kg non-returnable containers

AFCONA ADDITIVES

Web Site : [www.afcona.com](http://www.afcona.com)

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.