

AFCONA - 3581



Chemical Composition

Organically modified polysiloxane for aqueous systems.

Product general description

Silicone based levelling and anti-crater agent for aqueous coatings without influent of inter-coat adhesion.

Product Properties:

AFCONA – 3581 is the 50% solid version of AFCONA – 3580. AFCONA-3581 is an organically modified polysiloxane with very short chain repeatable units of siloxane. Due to the small molecules, they move very fast to a defected area. This gives very good anti-crater properties without any inter-coat adhesion problems.

AFCONA – 3581 is also widely uses in electroplating and electro deposition coating to avoid crater formation as well as giving a smooth, good leveling and good appearance coating. Itself is not an ionic structure, does it can be use in anionic and cationic system.

AFCONA-3581 is recommended to use in all kind of water-based coatings with a pH range of 4 - 10.

The use of AFCONA-3581 gives the following advantages:

- 1) Excellent anti-crater behavior.
- 2) Better substrate wetting.
- 3) Improved leveling.
- 4) No inter-coat adhesion problems.
- 5) little or no foam stabilization.

Note: the slip performance, due to the small molecules, is less.

Product Specification

Non-volatile matter	50 - 54% (120°C,0.5h)
Solvent	Methoxy Propanol
Flash point	35°C
Gardner color	Max.3
Appearance	Transparent to slight yellowish liquid (25°C)

Addition and dosage

0.1 – 1.0% on total formulation. In general, under normal conditions, the dosage is 0.1 – 0.3% based on total formulation.

Incorporation

AFCONA-3581 should be added prior to, or after processing.

Storage

AFCONA-3581 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 3 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 200 kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.