

AFCONA - 2041



Chemical Composition

Modified Polysiloxane defoamer, without fluorocarbon.

Product general description

A moderate defoamer with less side effects.

Product properties

AFCONA-2041 is the none fluorocarbon version of AFCONA – 2040. AFCONA – 2041 prevents the formation of foam and blisters during manufacturing and application. It has the combination of good defoaming as well as compatibility with most resin system. The compatibility with resins is slight lower than AFCONA - 2040.

AFCONA - 2041 is recommended for brush and conventional spray application.

The properties and application areas of AFCONA – 2041 as below:

- 1) Physical drying systems based on acrylic, Nitrocellulose, vinyl or chlorinated polymers
- 2) Polyurethane systems, for polyol resins based on Polyester, Polyacrylate, Polybutadien Glycol and Polypropylene Glycol
- 3) Solventless or solvent containing epoxy systems for floor, marine and heavy duty coatings
- 4) Not suitable for low polar systems, such as air dry alkyd.
- 5) Very good low temperature stability, long term storage below 0°C is possible.

Product Specification

Solvent	Butyl Acetate/SBP solvent
Density	0.80 – 0.84 g /cm ³ (20°C)
Refractive index	1.415 – 1.425(25°C)
Flash point	27°C
Appearance	Clear to slightly yellow liquid (25°C)

Addition and dosage

0.1 - 0.7% on total formulation. In general under normal conditions, the dosage is 0.2 – 0.5% based on total formulation.

Incorporation

To prevent foaming AFCONA-2041 can be added prior to processing. If it is added to the finished product, care must be taken to ensure uniform distribution.

Storage

AFCONA-2041 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

20kg and 150kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES
Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.